

CERFIX PROCOVER

Movement joints



DESCRIPTION

Procover G is a range of joint covers for level floors in commercial facilities or large constructions, such as load-bearing structures (floors for example) which need extra space to allow for the different movement of each of the elements.

In these contexts, the product conceals the separation between floor sections and hides any cutting or laying imperfections while allowing adjacent materials to expand.

G range models in silver anodized aluminium, and in different shapes and sizes, are recommended as a floor joint and cover, especially in commercial applications.

Models **750, 050, 760, 060, 780, 080, 7100, 0100** in stainless steel and polished brass are ideal as a floor joint and cover in domestic and commercial contexts.

MATERIALS

Anodized aluminium

Al-Mg-Si aluminium, heat-treated in T6 (6060 T6).

The profiles are made by extrusion then anodized with a $\geq 15 \mu\text{m}$ thick layer.

The outer surface must be protected from scratches and rubbing. They present a strong resistance to chemical and atmospheric agents. When wet, concrete and its derivatives produce alkaline substances which can corrode metal (forming aluminium hydroxide) when allowed to react with the surface. For this reason, the visible surface of the profile must be quickly and delicately cleaned to remove any concrete, adhesive or grouting substances and detergents.

Anodized surfaces can become ruined through wear and foot traffic (profiles used on floors) and the original finish lost as a result.

Stainless steel

AISI 430 - DIN 1.4016

This type of stainless steel has moderate resistance to corrosive agents. It is recommended for indoor use.

Polished brass

Alloy CW624N UNI EN 12167

The outer surface must be protected from scratches and rubbing.

Resistance to chemical agents and mechanical stress is good. Parts of the brass in contact with the air are subject to oxidation, producing a film on the surface. In the presence of extreme humidity or corrosive agents, brass will oxidise quickly and marks may appear on the surface. Where necessary, it can be restored to its natural state with abrasives or special polishes.

General note on metals

Aluminium, stainless steel and brass are not resistant to all chemical compounds. Consequently, contact with particularly aggressive products like hydrochloric acid (HCl) and phosphoric acid (H3PO4) should be avoided. Products generally used to clean stone, ceramic and porcelain tiles, such as muriatic acid, ammonia and bleach, damage the surface finish on the metal and can cause intense corrosion. Moreover, any residues of concrete, adhesive, and grouting materials must always be removed from the surface of the profiles as quickly and delicately as possible.

If adhesive tape is used to cover the profile, it must not be left any longer than an hour.

FIXING

Fixing with PP/96 type adhesive

Remove the profile from the packaging.

Where present, also remove any protection (protective and/or shrink-wrapped film) added to protect the finish.

Measure the length required and cut the profile to this length using an appropriate tool.

Place the profile, cut to the right length, in position and fix it to the laying surface with a suitable adhesive (such as PP/96), making sure that the support is free of dirt and perfectly clean.

Press and hold evenly along the length of the profile to make sure it bonds correctly to the laying surface.

Fixing profiles with adhesive

Remove the profile from the packaging.

Where present, also remove any protection (protective and/or shrink-wrapped film) added to protect the finish.

Measure the length required and cut the profile to this length using an appropriate tool.

Pull off the protective film making sure that the surface onto which it will be placed is perfectly clean and not flaking.

Lay the profile in position, press and hold evenly along the full length to make sure it bonds correctly to the laying surface.

CARE AND MAINTENANCE

Care and maintenance procedures for the materials used to make these profiles depends largely on the type of alloy and/or finish used.

The instructions provided below describe the operations to be performed on the profile to restore it as much as possible to its original condition.

The purpose of this document is to provide as many general indications as possible to guide you on when and how to clean the product, but they should also be verified on a case-by-case basis.

It should be pointed out there are specific responsibilities in each part of the product's life cycle, starting from when it is installed the first time.

Aluminium

No special maintenance is required and aluminium products can be easily treated with colourless alcohol in a water solution or using ordinary detergents, provided they do not contain acid (hydrochloric or hydrofluoric). Detergent products made by multiple manufacturers and sold under a variety of commercial brands can generally be used for cleaning.

Generally speaking, there are three types of products:

- Alkaline
- Neutral
- Acid

For cleaning purposes, we recommend using a neutral detergent diluted in water then rinsing with water only, using a non-abrasive sponge and/or cloth to avoid scratching and/or damaging the anodized surface. During cleaning, the following aspects must be kept in mind at all times:

- Do not use acid or alkaline detergents because they could damage the aluminium;
- Do not use products and/or abrasive materials;
- Do not use organic solvents on painted surfaces;
- Do not use detergents without first checking their chemical composition;
- Do not apply detergents straight onto the surface to be cleaned;
- Surfaces must be "cold" (max T° = 30°C) during cleaning and not exposed to direct sunlight;
- Detergents used in cleaning must also be "cold" (max T° = 30°C) and steam sprays should not be used.

In any case, the final stage in the cleaning process is always sufficient rinsing of the parts treated with water. They must then be immediately dried using soft fabric or leather cloths. Polishes or similar products are not required.

Clean profiles carefully as soon as required, following the instructions on the product package, to prevent any residues of concrete, grout or similar substances from attacking the surface.

Stainless steel

Stainless steel surfaces can be polished with suitable, widely available products.

Stainless steel is easy to clean and extremely hygienic; the smooth, non-porous surface makes the adhesion and survival of bacteria and/or other micro-organisms.

To keep stainless steel perfectly maintained, there are just a few simple rules: wash with soap and warm water, rinse well then dry with a soft cloth.

For surfaces exposed to atmospheric agents and attack, we recommend cleaning the stainless steel profile regularly to maintain the surface unaltered and prevent corrosion.

Surfaces with a brushed finish should always be cleaned in the direction of the brushing and not at an angle to it.

In the event of scratches, use a detergent/polish made specifically for stainless steel, and a soft cloth.

For cleaning, do not use any of the following:

- detergents containing hydrochloric acid (also known as muriatic acid), hydrofluoric acid or bleach; avoid direct contact on surfaces with detergents containing chlorides, unless the contact is short and the surface is well-rinsed afterwards.
- abrasive powdered detergents which could damage the surface finish of the profile.

Do not leave mild steel objects or utensils (like brushes or steel wool normally used to remove residues of mortar or similar products)

in contact with stainless steel profiles for extended lengths of time. They could transfer iron particles (contamination) and trigger rust on the surface.

Do not leave damp cloths or sponges for extended lengths of time on the stainless steel surface to prevent the formation of unsightly water marks.

Brass

Brass does not require special maintenance: it can be easily cleaned with alcohol diluted in water or ordinary detergents, provided they are not acid-based. Water can be used with added neutral detergents and the final rinse with water alone. Use non-abrasive sponges or cloths which will not scrape the surface. Use polishes that are commonly available.

FIRE PREVENTION MEASURES

In the event of fire, use chemical fire extinguishers, dry sand or solid extinguishing agents.


NOTES

These profiles must be handled with caution, being careful to wear suitable gloves to prevent injury and/or cuts to the hands.


The instructions and specifications provided here are the product of our experience but are only a guide, should not be considered exhaustive and must be confirmed by extensive practical applications.

Profilpas declines any responsibility for damage to people or things resulting from improper use of the product.


Users must establish for themselves if the product is suitable for the required use and they bear full responsibility for any incorrect installation of the material.




G/40/



G/60/



G/80/



GR/80/SF

PROCOVER



pack	20 pcs	20 pcs	6 pcs / blister	20 pcs
length cm	300	300	100	300
ART.	G/40/	G/60/	G/460/	G/80/
finishing	A	SF A	AD	SF A

ALUMINIUM

silver anodised	 74528	74558	74588	21982	74618	74648

art. G/40, G/60 and G/80 individually packed


PROCOVER

lengt = 270 cm - pack 10 pcs	L
width	80
ART.	GR/80/
finishing	SF

ALUMINIUM

silver anodised	 71855

individually packed

**PROCOVER**

pack	10 pcs	6 pcs / blister	10 pcs	6 pcs / blister	5 pcs	3 pcs / blister	5 pcs
length cm	300	100	300	100	300	100	300
width mm	50	50	60	60	80	80	100
thickness	12/10						
ART.	750/	4750/	760/	4760/	780/	4780/	7100/
finishing	SF A	AD	SF A	AD	SF A	AD	SF A

STAINLESS STEEL

polished stainless steel AISI 430 - DIN 1.4016		74818 74828	22090	74838 74848	40531	74858 74868	40553	74878 74888

art. 750/, 760/, 780/, 7100/ individually packed

PROCOVER

pack	10 pcs	6 pcs / blister	5 pcs	6 pcs / blister	5 pcs	3 pcs / blister	5 pcs.
length cm	300	100	300	100	300	100	300
width mm	50	50	60	60	80	80	100
thickness	13/10						
ART.	050/	4050/	060/	4060/	080/	4080/	0100/
finishing	SF A	AD	SF A	AD	SF A	AD	SF A

STAINLESS STEEL

polished		74738 74748	22050	74758 74768	40504	- 74788	40512	74798 74808

art. 050/, 060/, 080/, 0100/ individually packed

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement nor replace requirements per the TDS in effect at the time of the MAPEI product installation. For the most up-to-date TDS and warranty information, please visit our website at www.mapei.com. **ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED MAPEI WARRANTIES.**

Before using, the user must determine the suitability of our products for the intended use, and the user alone assumes all risks and liability. **ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.**

CONTACT INFORMATION

MAPEI Headquarters of North America

1144 East Newport Center Drive
Deerfield Beach, Florida 33442
1-888-US-MAPEI (1-888-876-2734) / (954) 246-8888

Technical Services

U.S. and Puerto Rico:

Flooring: 1-800-992-6273

Concrete and heavy construction: 1-888-365-0614

Canada:

1-800-361-9309

Customer Service

1-800-42-MAPEI (1-800-426-2734)

Edition Date: October 31, 2023 MK 13264 (24-2004)

For the most current product data and BEST-BACKEDSM warranty information,
visit www.mapei.com.

All Rights Reserved. © 2023 MAPEI Corporation.

