

Planigrout 755

Cement-Based, General-Purpose Construction Grout



DESCRIPTION

Planigrout® 755 is a one-component, nonmetallic, nonstaining, nonshrinking, cementitious construction grout consisting of select fine aggregates and special additives. *Planigrout* 755 requires only the addition of water to produce consistencies varying from dry pack to flowable.

FEATURES AND BENEFITS

- Highly versatile grout producing consistencies from dry pack to flowable
- Specially formulated to achieve high compressive and flexural strengths
- Ideal for structural grouting and anchoring

INDUSTRY STANDARDS AND APPROVALS

- Conforms to the physical requirements of ASTM C1107 and CRD – C621 standards

WHERE TO USE

- For load bearing and stabilization of base plates for columns and machinery
- For anchoring bolts and handrails
- For grouting under precast, cast-in-place, post-tensioned and pre-stressed concrete members

- For interior or exterior applications 1/2" to 2-3/8" (12 mm to 6 cm) on clean, properly prepared concrete substrates
- For jointing structural precast components and for filling rigid joints and keyways up to 2-3/8" (6 cm) thick

SUITABLE SUBSTRATES

- Properly prepared concrete at least 28 days old, structurally sound, stable and solid, with all loose materials removed

Consult MAPEI's Technical Services Department for installation recommendations regarding substrates and conditions not listed.

SURFACE PREPARATION

Reference ACI 351.1R-12, "Grouting between Foundations and Bases for Support of Equipment and Machinery"

- Thoroughly clean the surface of any substance that could interfere with the bond including dirt, paint, tar, asphalt, wax, oil, grease, curing compounds, form-release agents, laitance, loose mortar, toppings, foreign substances and any other residues.
- Concrete surfaces must be mechanically profiled and prepared by needle gun, grit-blasting, sandblasting, waterjetting, scarifying or other engineer-approved methods to obtain an International Concrete Repair Institute (ICRI) concrete surface profile (CSP) of #5 to #10.
- Concrete substrate and ambient room temperatures must be between 41°F and 95°F (5°C and 35°C) before application. Temperatures must be maintained within this range for at least 72 hours after the installation of *Planigrout 755*.
- Thoroughly saturate the concrete contact area for 24 hours before grouting. Do not apply over standing water; remove excess water prior to grouting. If a 24-hour period is not possible, then saturate with water for at least 4 hours, ensuring that surface water is removed before product placement.
- Steel baseplate should be mechanically cleaned to a near-white finish per SSPC-SP2.

MIXING

Before product use, take appropriate safety precautions. Refer to the Safety Data Sheet for details.

1. Into a clean mixing pail, pour 4/5 of the required amount of cool, clean, potable water (see "Application Properties" table below for mixing ratios).
2. Slowly add *Planigrout 755* to water while mixing, using a low-speed mixer. Add as much of the remaining 1/5 of water to achieve the desired consistency. Mix for up to 4 minutes, scraping down any unmixed powder after 1 to 2 minutes, and remix to a smooth, homogenous consistency.
3. Do not overmix.
4. Place immediately after mixing. Do not hand-mix *Planigrout 755*.
5. Do not mix more material than can be applied within 1 hour.

PRODUCT APPLICATION

Reference ACI 351.1R-12, "Grouting between Foundations and Bases for Support of Equipment and Machinery." Read all installation instructions thoroughly before installation.

1. a. Dry-pack consistency: *Planigrout 755* must be firmly pressed or rammed into place. Use metal or hardwood tamping tools and mallet.

b. Plastic consistency: *Planigrout 755* may be rodded, strapped, chained or troweled into areas where material cannot flow into place.

c. Flowable consistency: *Planigrout 755* may be used with a low-pressure, mechanical cement grout pump or poured in a flowable state into a proper head box for the area to be grouted, and hand-rodded or chained into place.
2. Apply to a maximum thickness of 2-3/8" (6 cm) neat. For deeper grouting application of up to 6" (15 cm) thick, add 30% by weight (16.5 lbs. [7.48 kg]) of cleaned and SSD 3/8" (10 mm) pea gravel.
3. To facilitate the filling of hard-to-reach areas, use a wood strip, steel rod or chain.
4. Do not vibrate *Planigrout 755*, as any required vibration should take place only on the construction forms.
5. Because *Planigrout 755* is designed for various consistencies and certain characteristics such as workability and mechanical strengths, a preliminary test or mockup should be performed to verify installation capabilities.

CURING

- Curing of exposed area is recommended for 72 hours after removal of forms using wet curing, damp burlap, polyethylene sheeting or a quality water-based curing compound.
- Protect from excessive heat and/or wind.
- Do not use solvent-based curing compounds.

CLEANUP

- Wash hands and tools promptly with water before material hardens.
- Cured material must be mechanically removed.

PROTECTION

- For at least 72 hours during initial curing, protect from direct sunlight, air movement and temperatures beyond application range.

LIMITATIONS

- Do not install over substrates containing asbestos.
- For thicker applications up to 6" (15 cm), extend 30% by weight (16.5 lbs. [7.48 kg]) with clean, washed and saturated surface-dry (SSD) 3/8" (10 mm) pea gravel
- *Planigrout 755* is prepackaged for easy field use and control, requiring only the addition of water. Add pea gravel for deeper applications. Do not add other additives or cements to *Planigrout 755*.

- *Planigrout 755* must be protected from freezing during its setting and hardening time. The minimum temperature during and 72 hours after application is 41°F (5°C).
- Although cracking can develop at the grout's shoulders, this does not affect product performance. Cracks can be treated to prevent penetration by water and other contaminants. Contact MAPEI's Technical Services Department for product recommendations.

Product Performance Properties

Laboratory Tests		Results	
		Dry-pack consistency	Plastic consistency
Flowable consistency			
Compressive strength – ASTM C109 (CAN/CSA-A5)*			
1 day		7,200 psi (49.7 MPa)	3,450 psi (23.8 MPa)
3 days		9,300 psi (64.1 MPa)	5,900 psi (40.7 MPa)
7 days		11,000 psi (75.9 MPa)	7,300 psi (50.3 MPa)
28 days		13,400 psi (92.4 MPa)	9,000 psi (62.1 MPa)
Flow table – ASTM C230		Forms a ball	110%
Freeze/thaw resistance – ASTM C666, Procedure A, 300 cycles		Durability factor of 98%	
Scaling resistance – ASTM C672, 50 cycles		Loss of 0.04 kg per m ²	
Volumetric change – ASTM C1090		0.0% to +0.3% at 28 days	
VOC content		0 g per L	

* The data shown is typical for controlled laboratory conditions. Reasonable variation from these results can be expected due to interlaboratory precision and bias. When testing the field-mixed material, other factors such as variations in mixing, water content, temperature and curing conditions should be considered.

Shelf Life and Product Characteristics

before mixing

Shelf life	1 year when stored in original, unopened packaging at 73°F (23°C)
Physical state	Powder
Color	Gray

Protect containers from freezing in transit and storage. Provide for heated storage on site and deliver all materials at least 24 hours before work begins.

Application Properties

	Dry-pack consistency	Plastic consistency	Flowable consistency
Mixing ratio (water per 50-lb. [22.7-kg] bag)	6.75 U.S. pints (3.19 L)	9.9 U.S. pints (4.68 L)	10.75 U.S. pints (5.09 L)
Pot life	Not applicable	60 minutes	60 minutes
Initial set – ASTM C191	2.5 hours	4.5 hours	6 hours
Final set – ASTM C191	3 hours	6 hours	7.5 hours
Application temperature range	41°F to 95°F (5°C to 35°C)		
Thickness per lift (neat)	1/2" to 2-3/8" (12 mm to 6 cm)		

Packaging

Size
Bag: 50 lbs. (22.7 kg)

Approximate Coverage**
per 50 lbs. (22.7 kg)

Consistency	Coverage
Dry pack	0.41 cu. ft. (0.0116 m ³)
Plastic	0.45 cu. ft. (0.0127 m ³)
Flowable	0.47 cu. ft. (0.0133 m ³)

** Coverage shown is for estimating purposes only. Actual jobsite coverage may vary according to substrate conditions and setting practices.

RELATED DOCUMENTS

- Grouting between Foundations and Bases for Support of Equipment and Machinery – ACI 351.1R-12

ADDITIONAL INFORMATION

Refer to the Safety Data Sheet (SDS) for specific data related to health and safety as well as product handling.

For information on MAPEI's commitment to sustainability and transparency, as well as how MAPEI products may contribute to green building standards and certification systems, contact sustainability_USA@mapei.com (USA) or sustainability-durabilite@mapei.com (Canada).

WARNING

The test results shown in the TECHNICAL DATA table were obtained in compliance with test methods and curing cycles, if applicable, defined in the industry standards referenced on the Technical Data Sheet. Please note that the use of test procedures or methods other than those indicated in the table could lead to different values and that, in such cases, any liability of our company is excluded.

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement nor replace requirements per the TDS in effect at the time of the MAPEI product installation. For the most up-to-date TDS and warranty information, please visit our website at www.mapei.com. **ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED MAPEI WARRANTIES.**

Before using, the user must determine the suitability of our products for the intended use, and the user alone assumes all risks and liability. **ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.**

CONTACT INFORMATION

MAPEI Headquarters of North America

1144 East Newport Center Drive
Deerfield Beach, Florida 33442
1-888-US-MAPEI (1-888-876-2734) / (954) 246-8888

Technical Services

U.S. and Puerto Rico:
Flooring: 1-800-992-6273
Concrete and heavy construction: 1-888-365-0614
Canada:
1-800-361-9309

Customer Service

1-800-42-MAPEI (1-800-426-2734)

Edition Date: January 19, 2026 MK 3000154 (25-3215)

For the most current product data and BEST-BACKEDSM warranty information,
visit www.mapei.com.
All Rights Reserved. © 2026 MAPEI Corporation.

