

MAPEI Gym Prep Primer

Fast-Drying, Textured Primer for Sports Substrates



DESCRIPTION

MAPEI Gym Prep Primer is a low-VOC, high-performance, water-based primer. It is designed to boost the performance of self-leveling underlayments over MAPEI Gym Prep Sealer and other nonporous substrates.

FEATURES AND BENEFITS

- Dries quickly, in 1 to 2 hours, depending on environmental conditions
- High bond to 100%-solids, epoxy moisture-control membranes
- Low in odor and VOCs for use in interior, occupied environments

WHERE TO USE

- Approved for use over properly installed, completely cured, 100%-solids, epoxy moisture barriers
- Approved for use over properly prepared nonporous substrates
- For use in interior athletic applications (schools, fitness centers, recreational facilities and professional sports centers)

LIMITATIONS

- For moisture limits on this primer, refer to the moisture limits of the product to be applied over it.
- Do not install over any substrates containing asbestos.
- Substrate and ambient temperatures must be between 50°F to 90°F (10°C to 32°C).
- In all cases, the surface temperature of the prepared concrete slab must be at least 5 degrees Fahrenheit (2.8 degrees Celsius) above the dew point to avoid condensation on the concrete surface as *MAPEI Gym Prep Primer* dries.
- Verify that the substrate is free of bond-inhibiting or bond-breaking materials such as curing compounds and dust.
- For use only in dry, interior environments. Do not apply on wet substrates.
- Do not dilute. Use at full strength for all applications.

SUITABLE SUBSTRATES

- Properly installed, 100%-solids, epoxy moisture barriers such as *MAPEI Gym Prep Sealer*
- Epoxy and cement terrazzo
- Poured epoxy flooring
- Sound and stable concrete substrates, whether smooth/nonporous or profiled/porous

Consult MAPEI's Technical Services Department for installation recommendations regarding any substrates and conditions not listed.

SURFACE PREPARATION

- All substrates must be structurally sound, dry, solid and stable.
- Thoroughly clean all surfaces of any substance that could interfere with the bond of the installation material, including dirt, paint, tar, asphalt, wax, oil, grease, latex compounds, sealers, curing compounds, form release agents, laitance, loose toppings, foreign substances and adhesive residues.

For details on proper surface preparation, refer to MAPEI's reference guide "Surface-preparation requirements for self-leveling underlayments" in the Concrete Restoration Systems section of MAPEI's Website.

MIXING

Before product use, take appropriate safety precautions. Refer to the Safety Data Sheet for details.

- *MAPEI Gym Prep Primer* is ready to use; no dilution is required.
- Before use, shake in case any settling has occurred during shipment or storage.

PRODUCT APPLICATION

Read all installation instructions thoroughly before installation.

1. Do not pour *MAPEI Gym Prep Primer* directly on the subfloor. Use a paint tray and apply using a dip-and-roll method.
2. Apply product with a 1/4" (6 mm) nap roller. Ensure that the surface receives a complete, thin film of product. Do not over-apply or puddle *MAPEI Gym Prep Primer*, as this will have a negative effect on drying time and potentially lead to poor bond performance.
3. An underlayment can typically be applied after 1 to 2 hours. Drying times will vary depending on porosity of surface, temperature and humidity.
4. As long as the surface of *MAPEI Gym Prep Primer* is clean and undamaged, there is no time limitation for underlayment application. If the cured *MAPEI Gym Prep Primer* surface becomes damaged or dirty, an additional thin coat may be applied.

CLEANUP

- Clean equipment immediately with water.
- Mineral spirits may be used to remove *MAPEI Gym Prep Primer* that has dried on tools.

Product Performance Properties

Laboratory Tests	Results
Solids content	57% to 61%
VOC content (SCAQMD Rule 1113)	< 100 g per L
Typical VOC content per SCAQMD Rule 1113 testing methods	0 g per L
pH	7.5 to 8.5
Density	1.1 to 1.3 g per mL

Shelf Life and Product Characteristics before mixing

Shelf life	2 years when stored in original, unopened packaging at 73°F (23°C)
Consistency	Pourable liquid
Polymer type	Acrylic
Color	Light yellow

Protect containers from freezing in transit and storage. Provide for heated storage on site and deliver all materials at least 24 hours before work begins.

Application Properties
at 73°F (23°C) and 50% relative humidity

Application temperature range	50°F to 90°F (10°C to 32°C)
Waiting time for application of self-leveling underlayments	1 to 2 hours
Flash point (Seta)	> 212°F (100°C)

CSI Division Classification

Cast Underlayment	03 54 00
-------------------	----------

Approximate Coverage*
per 2 U.S. gals. (7.57 L)

Typical Application Tool	Coverage
1/4" (6 mm) nap roller	1,200 to 1,400 sq. ft. (111 to 130 m ²)

** Coverage depends on the substrate profile and porosity.*

Packaging

Size
Jug: 2 U.S. gals. (7.57 L)



RELATED DOCUMENTS

- Reference guide: "Surface preparation requirements for self-leveling underlayments**

**At www.mapei.com

ADDITIONAL INFORMATION

Refer to the SDS for specific data related to health and safety as well as product handling.

For information on MAPEI's commitment to sustainability and transparency, as well as how MAPEI products may contribute to green building standards and certification systems, contact sustainability_USA@mapei.com (USA) or sustainability-durabilite@mapei.com (Canada).

WARNING

The test results shown in the TECHNICAL DATA table were obtained in compliance with test methods and curing cycles, if applicable, defined in the industry standards referenced on the Technical Data Sheet. Please note that the use of test procedures or methods other than those indicated in the table could lead to different values and that, in such cases, any liability of our company is excluded.

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement nor replace requirements per the TDS in effect at the time of the MAPEI product installation. For the most up-to-date TDS and warranty information, please visit our website at www.mapei.com. **ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED MAPEI WARRANTIES.**

Before using, the user must determine the suitability of our products for the intended use, and the user alone assumes all risks and liability. **ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.**

CONTACT INFORMATION

MAPEI Headquarters of North America

1144 East Newport Center Drive
Deerfield Beach, Florida 33442
1-888-US-MAPEI (1-888-876-2734) / (954) 246-8888

Technical Services

U.S. and Puerto Rico:

Flooring: 1-800-992-6273

Concrete and heavy construction: 1-888-365-0614

Canada:

1-800-361-9309

Customer Service

1-800-42-MAPEI (1-800-426-2734)

Edition Date: July 29, 2024 MK 3000500 (24-2197)

For the most current product data and BEST-BACKEDSM warranty information,
visit www.mapei.com.
All Rights Reserved. © 2024 MAPEI Corporation.

