

Mapecoat TNS Base Coat Binder Tex

Factory-Textured, Fast-Set, Acrylic Resurfacer



DESCRIPTION

Mapecoat™ TNS Base Coat Binder Tex is a factory-textured, flexible, fast-set, 100% acrylic latex resurfacer for indoor and outdoor surfaces, used as a basecoat to prepare asphalt and pretreated concrete surfaces before applying additional *Mapecoat TNS* products. *Mapecoat TNS Base Coat Binder Tex* is ideal for covering small imperfections in the substrate and for promoting a strong bond. *Mapecoat TNS Base Coat Binder Tex* is used with *Mapecoat TNS* system products to form durable and comfortable playing surfaces.

FEATURES AND BENEFITS

- Sand is added to this product at the factory to ensure quality and consistency
- Eliminates the need to source and handle bags of silica sand
- Ideal for covering small imperfections in the substrate
- Environmentally friendly and does not require the handling of dry silica sand

WHERE TO USE

- Basecoat for indoor and outdoor surfaces to prepare asphalt and pre-treated concrete surfaces before applying additional *Mapecoat TNS* products
- Basecoat over pre-treated existing acrylic surfaces before applying additional *Mapecoat TNS* products

LIMITATIONS

- Concrete floors must be completely cured (at least 28 days) and free from hydrostatic pressure and alkaline conditions.
- Do not install when the moisture vapor emission rate (MVER) of the concrete substrate exceeds 8 lbs. per 1,000 sq. ft. (3.63 kg per 92.9 m²) per 24 hours, when using the anhydrous calcium chloride test (ASTM F1869).
- Do not install when the relative humidity of the concrete substrate exceeds 85% (ASTM F2170).
- Do not apply when rain is imminent.
- Do not apply over damp or wet surfaces.
- Apply only when the ambient temperature is between 50°F and 95°F (10°C and 35°C).
- Do not apply if the surface temperature is lower than 50°F (10°C).
- Do not apply if the level of ambient humidity is higher than 85%.
- Do not apply directly on concrete. Only apply after treating the surface with a coat of *Mapecoat TNS Primer EPW*.

SUITABLE SUBSTRATES

- Cured concrete
- Cured asphalt (in 15 to 20 sunshine days above 73°F or 23°C)

Consult MAPEI's Technical Services Department for installation recommendations regarding substrates and conditions not listed.

SURFACE PREPARATION

- For base construction and paving substrate specifications, refer to the American Sport Builders Association (ASBA), United States Tennis Association (USTA), International Tennis Federation (ITF), National Asphalt Pavement Association (NAPA) and American Concrete Institute (ACI) guidelines.
- All concrete substrates must be primed with *Mapecoat TNS Primer EPW*.
- The substrate must be clean and free of dust, dirt, oil, grease, paint, curing agents, concrete sealers, loosely bonded toppings, loose particles, old coating residues, and any other substance or condition that may prevent or reduce adhesion.
- All defects (potholes, popouts and other large defects) must be leveled and treated accordingly before *Mapecoat TNS Base Coat Binder Tex* is applied.

PRODUCT PREPARATION

Before product use, take appropriate safety precautions. Refer to the Safety Data Sheet for details.

- *Mapecoat TNS Base Coat Binder Tex* should be pre-mixed with a low-speed mechanical mixer before dilution.
- Once pre-mixed, the drum contents should be split into 15-gallon (56.8-L) halves. Dilute each half with 5 to 6 U.S. gals. (18.9 to 22.7 L) of clean, potable water (depending on temperature and installer preference). The diluted product should be mixed until fully smooth and homogeneous (the sides of the drum may need to be scraped to fully mix all material). It is important to keep the mixture homogeneous by occasional remixing during the application process.



PRODUCT APPLICATION

- Apply *Mapecoat TNS Base Coat Binder Tex* with a flexible rubber squeegee (50 or 70 durometer).

CLEANUP

- Clean tools with water while the product is still fresh/wet. Any dried or cured material must be removed mechanically.

PROTECT FROM FREEZING.

Product Performance Properties

Laboratory Tests	Results
Density	11.22 lbs. per gal. (1.34 kg per L)
VOC content (SCAQMD Rule 1113)	<100 g per L
Typical VOC content per SCAQMD Rule 1113 testing methods	2 g per L
Drying time	1 to 2 hours at 73°F (23°C) and 50% relative humidity. Note that low temperatures and high humidity will extend drying time.

Shelf Life and Product Characteristics before mixing

Shelf life	2 years when stored in dry conditions in original, unopened packaging at 73°F (23°C)
Physical state	Thick liquid

Mixing Ratio

Product Amount	Water Amount
15 U.S. gals. (one half drum) or 56.8 L	5 to 6 U.S. gals. (18.9 to 22.7 L)

Packaging

Size
Drum: 30 U.S. gals. (114 L)

Approximate Coverage*

undiluted

Coat	Coverage in sq. ft. per U.S. gal.	Coverage in sq. yd. per U.S. gal.	Coverage in m ² per L
First coat (fresh asphalt)	80 to 90	0.1 to 0.11	1.96 to 2.20
Second coat (or recoat)	90 to 110	0.08 to 0.1	2.20 to 2.69

* Coverage shown is for estimating purposes only. Actual jobsite coverage may vary according to substrate conditions and application techniques.

ADDITIONAL INFORMATION

Refer to the Safety Data Sheet (SDS) for specific data related to health and safety as well as product handling.

For information on MAPEI's commitment to sustainability and transparency, as well as how MAPEI products may contribute to green building standards and certification systems, contact sustainability_USA@mapei.com (USA) or sustainability-durabilite@mapei.com (Canada).

WARNING

The test results shown in the TECHNICAL DATA table were obtained in compliance with test methods and curing cycles, if applicable, defined in the industry standards referenced on the Technical Data Sheet. Please note that the use of test procedures or methods other than those indicated in the table could lead to different values and that, in such cases, any liability of our company is excluded.

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement nor replace requirements per the TDS in effect at the time of the MAPEI product installation. For the most up-to-date TDS and warranty information, please visit our website at www.mapei.com. **ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED MAPEI WARRANTIES.**

Before using, the user must determine the suitability of our products for the intended use, and the user alone assumes all risks and liability. **ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.**

CONTACT INFORMATION

MAPEI Headquarters of North America

1144 East Newport Center Drive
Deerfield Beach, Florida 33442
1-888-US-MAPEI (1-888-876-2734) / (954) 246-8888

Technical Services

U.S. and Puerto Rico:

Flooring: 1-800-992-6273

Concrete and heavy construction: 1-888-365-0614

Canada:

1-800-361-9309

Customer Service

1-800-42-MAPEI (1-800-426-2734)

Edition Date: June 12, 2025 MK 3000541 (25-1746)

For the most current product data and BEST-BACKEDSM warranty information,
visit www.mapei.com.

All Rights Reserved. © 2025 MAPEI Corporation.

