

Mapeair N

Natural Air-Training Agent

FOR PROFESSIONAL USE ONLY

DESCRIPTION

Mapeair N is a natural air-entraining agent that provides a stable air-void system in plastic and hardened concrete. This stable air-void system is essential for producing freeze/thaw-durable concrete. *Mapeair N* meets or exceeds the requirements of ASTM C260, Standard Specification for Air Entraining Admixture for Concrete.

FEATURES AND BENEFITS

- Natural air-entraining agent
- Meets ASTM C260
- Meets AASHTO M154

WHERE TO USE

Mapeair N provides excellent durability in freeze/thaw applications due to consistent bubble size and spacing in hardened concretes.

It may be used also for the following applications:

- To improve resistance to salt scaling and sulfate-related deterioration
- To reduce bleeding and segregation and to increase the workability of a concrete mix
- To aid the finish of concrete, reduce “bug holes” and produce more even, smoother surfaces
- To aid the pumping of lean concretes
- To aid in placing low-slump concrete mixes (paving)

Mapeair N is a consistent and effective air-entraining agent when used with low-alkali cements, fly ash and/or other supplementary cementitious materials.

APPLICATION PROCEDURE

Mapeair N may be added together with the mixing water or directly into the sand. Once the remaining materials are added, thoroughly mix the concrete to generate proper air entrainment.

Concrete mixtures should be tested regularly with air meters during production to verify that the air content meets the technical requirements and project specifications.

COMPATIBILITY WITH OTHER PRODUCTS

Mapeair N is compatible with most MAPEI products for preparing quality concrete. It is especially compatible with:

- Mid- and high-range water reducers from the *Mapeplast* and *Dynamon*® product families.
- Non-chloride accelerators.
- Retarders and slump extenders.
- Viscosity-modifying admixtures.
- Silica-fume-based powder additions.
- Fly ash and any other kind of cementitious addition.
- All types of Portland cements, including low-alkali cements.

MAPEI's Technical Services Department is available to evaluate which admixture or admixture package is most suitable for any specific need. Contact MAPEI's Technical Services Department for further advice.

DOSAGE RATES

The recommended dosage of *Mapeair N* is 0.65 to 3.0 U.S. oz. per 100 lbs. (42 to 195.6 mL per 100 kg) of cementitious materials. Field tests will determine the proper dosage for each set of materials.

Contact MAPEI's Technical Services Department for recommended dosages and for assistance when using the product.

PACKAGING

Mapeair N is available by bulk delivery, in 5-U.S.-gal (18.9-L), 55-U.S.-gal. (208-L) drums and 275-U.S.-gal. (1 040-L) totes.

STORAGE

Mapeair N can be stored for 1 year in the original sealed containers. Protect from freezing.

Technical Data

Consistency	Liquid
Color	Light yellow
Density	8.44 lbs./gal. (1.01 kg/L)
Primary function	Air-entraining
Density	8.44 lbs./gal. (1.01 kg/L)

ADDITIONAL INFORMATION

Refer to the Safety Data Sheet (SDS) for specific data related to health and safety as well as product handling.

For information on MAPEI's commitment to sustainability and transparency, as well as how MAPEI products may contribute to green building standards and certification systems, contact sustainability_USA@mapei.com (USA).

WARNING

The test results shown in the TECHNICAL DATA table were obtained in compliance with test methods and curing cycles, if applicable, defined in the industry standards referenced on the Technical Data Sheet. Please note that the use of test procedures or methods other than those indicated in the table could lead to different values and that, in such cases, any liability of our company is excluded.

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement nor replace requirements per the TDS in effect at the time of the MAPEI product installation. For the most up-to-date TDS and warranty information, please visit our website at www.mapei.com. **ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED MAPEI WARRANTIES.**

Before using, the user must determine the suitability of our products for the intended use, and the user alone assumes all risks and liability. **ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.**

CONTACT INFORMATION

MAPEI Headquarters of North America

1144 East Newport Center Drive
Deerfield Beach, Florida 33442
1-888-US-MAPEI (1-888-876-2734) / (954) 246-8888

Technical Services

U.S. and Puerto Rico:

Flooring: 1-800-992-6273

Concrete and heavy construction: 1-888-365-0614

Canada:

1-800-361-9309

Customer Service

1-800-42-MAPEI (1-800-426-2734)

Edition Date: January 9, 2026 MK 3000573 (25-3237)

For the most current product data and BEST-BACKEDSM warranty information,
visit www.mapei.com.
All Rights Reserved. © 2026 MAPEI Corporation.

