

	BROADCAST SYSTEMS				EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY- LICS
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST (CRYLAFLOR)	
3M [™] Duraprep	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	SD	SD	TS	TS	NR	SD	TS	SD	TS	TS	SD	SD	SD	SD	SD	SD
3M [™] Stainless Steel	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS
AC-103 - 100%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	SD	TS	TS	TS	TS	TS	OK	TS	TS	SD	TS	OK	SD	OK	OK
Acetaldehyde	TS	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Acetic Acid - 3%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	OK
Acetic Acid - 5%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	OK	TS	TS	OK	TS	TS	TS	TS
Acetic Acid - 10%	SD	OK	OK	OK	SD	OK	SD	SD	SD	SD	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	TS	OK	OK	OK
Acetic Acid - 30%	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	SD	SD	OK	TS	SD	OK	TS	TS	SD	SD	TS	SD	TS	OK	SD	SD	SD
Acetic Acid - 50%	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	NR	NR	NR	TS	SD	OK	TS	TS	SD	SD	TS	SD	TS	SD	SD	NR	NR
Acetic Acid (50%) to Glacial (100%)	TS	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Acetic Anhydride	TS	TS	TS	SD	NR	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Acetone - 10%	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Acetone - 100%	SD	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	NR	NR	NR	TS	SD	OK	OK	TS	OK	SD	TS	OK	TS	OK	OK	NR	NR
Acetyl Chloride - 100%	TS	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Acidulate 45T	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	SD	TS	TS	NR	TS	TS	TS	TS
ACP-99 Ketone	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR
Acrylic Acid - 100%	TS	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Acrylonitrile	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS
Adipic Acid - 25%	TS	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Allyl Alcohol	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Allyl Chloride	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS
Alum - 48%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	OK	OK
Alum (Saturated Solution)	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Aluminum Bromide	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Aluminum Chloride	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Aluminum Nitrate (Saturated)	TS	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS			EPOXY COATINGS													URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS	
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELE [™] 4850	ACCELE [™] 5	ACCELE [™] (REGULAR, EXT, LH)	ACCELE [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST	MMA COATINGS (CRYLAFLOR)
Aluminum Sulfate	TS	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Aminoethanolamine	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	SD	
Ammonia - 10%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	OK	TS	TS	OK	TS	TS	TS	TS	
Ammonia - 30%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	
Ammonia (Wet Gas)	OK	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Ammonium Bisulfite	OK	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Ammonium Chloride	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Ammonium Cocoampholyte - 30%	SD	TS	TS	OK	TS	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Ammonium Fluoride	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Ammonium Hydroxide - 20%	OK	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Ammonium Hydroxide - 30%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	SD	
Ammonium Hydroxide - 38%	OK	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Ammonium Lauryl Sulfate - 30%	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Ammonium Nitrate	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	OK	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Ammonium Persulfate	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Ammonium Sulfate	TS	TS	TS	TS	OK	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Ammonium Sulfide	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Ammonium Sulfite	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Ammonium Xylene Sulfonate - 40%	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Amyl Acetate	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Amyl Alcohol	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	NR	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Aniline	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	
Aniline Hydrochloride	TS	TS	TS	SD	TS	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Antifreeze	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	OK	OK	TS	OK	TS	TS	OK	TS	OK	OK	OK	
Antimony Chloride (Tri)	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Aqua Regia	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS			EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS				
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST	MMA COATINGS (CRYLAFLOR)		
Aromatic 100	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS			
Aromatic Hydrocarbons-Super Hiflash 100	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS			
Arsenous Acid	TS	TS	TS	SD	TS	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS		
Assurance	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS			
Avance Grease Cutter	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	OK	TS	TS	TS	OK	TS	SD	SD	OK		
Avance Pot and Pan Detergent	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	SD	OK	OK			
Barium Chloride	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS		
Barium Hydroxide	OK	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS		
Barium Sulfate	OK	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS		
Barium Sulfide	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS		
BC-250 Diesel Fuel Biocide	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS			
Beer	SD	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS			
Benzal Chloride	TS	TS	TS	NR	OK	NR	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	NR	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS		
Benzaldehyde	TS	TS	TS	OK	OK	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS		
Benzene (Benzol)	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	NR	NR	NR	TS	SD	SD	TS	TS	TS	TS	SD	TS	OK	TS	NR	TS	NR		
Benzene Sulfonic Acid - 50-100%	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS			
Benzene Thiol	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS			
Benzoic Acid (Saturated)	SD	TS	TS	OK	TS	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS			
Benzoyl Chloride	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS			
Benzyl Alcohol	SD	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	SD	TS	TS	OK	TS	TS	NR	TS	SD	SD	NR			
Benzyl Chloride	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS			
Betadine - 10%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	SD	SD	TS	SD	TS	TS	SD	SD	SD	SD	SD			
Betco Quat-Stat 5	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS			
Black Liquor (Paper)	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS			
Bleach - 5%	SD	OK	OK	OK	SD	OK	OK	SD	SD	SD	SD	OK	TS	TS	TS	SD	OK	OK	OK	OK	SD	OK	OK	OK	TS	TS	TS			
Boric Acid - 4%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	OK			

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS				EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY- LICS
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST	MMA COATINGS (CRYLAFLO [™])
Boric Acid (Saturated)	SD	TS	TS	OK	TS	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Brake Fluid	TS	OK	OK	OK	NR	OK	NR	NR	NR	NR	NR	SD	SD	SD	TS	TS	SD	SD	OK	OK	OK	SD	NR	SD	TS	SD	NR	OK
Brine	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Bromine, Dry Gas	TS	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Bromine, Wet Gas	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Bromine Water - 5%	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Butanol Normal	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS	NR	TS	NR
Butyl Acetate	SD	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Butyl Acid Levulinic	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Butyl Acrylate	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Butyl Alcohol	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	NR
Butyl Amine	SD	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Butyl Carbitol	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR
Butyl Carbitol Acetate	TS	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Butyl Cellosolve	TS	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR
Butyl Cellosolve Acetate	TS	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	NR	NR	NR	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	NR
Butyl Ether	SD	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Butyric Acid - 100%	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Cadmium Chloride	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Cadmium Plating - Cyanide	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Calcium Bisulfite	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Calcium Chloride	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Calcium Hydroxide	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Calcium Hypochlorite - 5%	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Calcium Nitrate	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Calcium Sulfate	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS				EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY- LICS
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST	MMA COATINGS (CRYLAFLOR)
Calcium Sulfite	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Caprylic Acid (Octanoic Acid)	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Carbolic Acid (Phenol) - 88%	TS	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Carbon Bisulfide (Di) Fumes (Wet)	TS	TS	TS	TS	SD	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Carbon Dioxide Gas	SD	TS	TS	SD	TS	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Carbon Tetrachloride	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	OK	OK	OK	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	NR	TS
Castor Oil	SD	TS	TS	SD	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Caustic Soda Solution	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	TS	OK	TS	OK	OK	OK	OK
Cellosolve	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Cellosolve Acetate	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Chloroacetic Acid - 1-20%	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Chloroacetic Acid - 20-50%	TS	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Chloroacetic Acid - 50-100%	TS	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Chloraprep [™] One-Step - 2%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	SD	TS	TS	TS	TS	SD	TS	TS	TS	OK	TS	SD	SD	OK	OK
Chlorine Bleach 2000	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	SD	TS	TS	TS	TS	OK	TS	TS	TS	OK	TS	SD	OK	OK	OK
Chlorine Dioxide Solution	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Chlorine Gas - Dry	SD	TS	TS	SD	NR	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Chlorine Gas - Wet	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Chlorine Water - Saturated	SD	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Chlorobenzene (Mono)	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Chlorobutane	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Chloroform	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Chlorophenol	SD	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Chlorosulfonic Acid	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Chlorotoluene	TS	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Chrome Plating 20-48 oz/gal	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
*Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
TS = Contact Tech Service Department

NR = Not recommended
† = May cause discoloration

	BROADCAST SYSTEMS			EPOXY COATINGS													URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY- LICS
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST (CRYLAFLOR)	
Chromic Acid - 10%	SD	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	SD	SD	TS	SD	OK	TS	TS	SD	SD	TS	SD	TS	SD	SD	SD	
Chromic Acid - 40%	TS	TS	TS	TS	TS	T S	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	TS	SD	
Chromic Chloride	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
CIP 100 Cleaner - 100%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	OK	OK	TS	OK	OK	TS	OK	TS	TS	OK	OK	OK	OK	
CIP 200 Cleaner - 100%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	SD	NR	TS	SD	TS	TS	SD	OK	SD	SD	
CIP 220 Cleaner - 100%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	SD	SD	TS	SD	TS	TS	SD	TS	SD	SD	
CIP 300 Cleaner - 100%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	
Citric Acid - 10%	SD	OK	OK	OK	OK	OK	OK	SD	SD	SD	OK	OK	OK	OK	OK	TS	SD	OK	OK	OK	OK	SD	OK	TS	TS	OK	OK	
Citric Acid - 20%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	OK	OK	
Citric Acid - 50%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	OK	OK	
Clidox-S	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	OK	TS	TS	OK	TS	TS	TS	
Clidox-S (1:18:1 Mix with Water)	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Clidox-S (1:5:1 Mix with Water)	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Clorox® - 10%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	
Coffee	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	
Cola - 90C	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	SD	SD	
Cola - Room Temp	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	
Copper Chloride	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	SD	SD	SD	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	SD	TS	
Copper Nitrate	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	
Copper Plating - Acid	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	
Copper Plating - Cyanide	SD	TS	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	
Copper Sulfate	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	OK	TS	TS	TS	TS	OK	TS	TS	TS	SD	TS	
Corn Oil	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	
Cottonseed Oil	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	
Coulter TruColor Wright Stain	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	SD	SD	
Cresol (Cresylic Acid)	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

				BROADCAST SYSTEMS		EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY-LICS
				RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	
Cresylic Acid	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS
Cumene	SD	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS
Cyclohexane	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS
Cyclohexanone	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	SD	SD	SD	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	SD	TS	OK		
Cymene	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS
Decon-Quat® 100	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS		
Decon-Quat® 200C	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS		
Decon-Spore 200® Plus	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS		
Detergent, Heavy Duty	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	OK	OK	OK		
Dextrose	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS
Diacetone Alcohol	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	
Dibromopropane Phosphate	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS
Dibutyl Phthalate	TS	TS	TS	OK	TS	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS
Dichloro Acetic Acid - 20%	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Diethanolamine	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Diethylene Chloroformate	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Diethylketone - 100%	TS	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Dimethyl Aniline	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS
Dimethyl Carbamoyl Chloride	TS	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS
Dimethyl Carbonyl Chloride	NR	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS
Dimethyl Ethanol Amine	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Dimethyl Formamide	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS
Dimethyl Sulfoxide	TS	TS	TS	SD	TS	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Dimethylamineborane	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Dimethylaminopropylamine	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS
Dinitro Benzene	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS			EPOXY COATINGS													URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS	
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HT'S 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	MMA COATINGS (CRYLAFLOR)	
Dinitro Toluene	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
DMF	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	OK	TS	TS	OK	TS	NR	SD	SD	SD
Docosanic Acid (in Ethanol) - 2.5%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS
Dodecyl Alcohol (Lauryl)	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Drano® (Sodium Hydroxide and Aluminum)	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	OK	TS	TS	TS	TS	OK	OK	TS	TS
Dyclean	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS
Ecolab AC-101 - 1%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab AC-101 - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab AC-3 Cleaner	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	NR	SD	SD
Ecolab AC-55-5 - 2%	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	TS	OK	TS	NR	TS	TS	TS	TS
Ecolab AC-55-5 - 100%	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	TS	TS	SD	TS	NR	TS	TS	TS	TS
Ecolab Active OX+™ - 1%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Active OX+™ - 100%	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	OK	TS	SD	TS	TS	TS	TS
Ecolab Advantis™ SM FC - 2%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Advantis™ SM FC - 100%	TS	TS	TS	TS	TS	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Boost™ 3200-Disinfectant Cleaner - 10%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Boost™ 3200-Disinfectant Cleaner - 100%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Boost™ 3201-Adjuvant - 10%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Boost™ 3201-Adjuvant - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Boost™ 3201 SM-Adjuvant - 10%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Boost™ 3201 SM-Adjuvant - 100%	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Boost™ Surface Treatment	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab CD 249 - 5%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab CD 249 - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS				EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY- LICS
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELER [™] 4850	ACCELER [™] 5	ACCELER [™] (REGULAR, EXT, LH)	ACCELER [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST	MMA COATINGS (CRYLAFLO [™])
Ecolab Conquest [™] K - 1%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Conquest [™] K - 100%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab DrySan [™] Duo	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Enforce K - 2%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Enforce K - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Enforce LP - 2%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Enforce LP - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Enviro San - 2%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Enviro San - 100%	TS	TS	TS	TS	TS	NR	NR	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Envirocid - 1%	TS	TS	TS	TS	TS	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	OK	TS	SD	TS	TS	TS	TS
Ecolab Envirocid - 100%	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	SD	TS	SD	TS	TS	TS	TS
Ecolab Exelerate [™] CIP+ - 2%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Exelerate [™] CIP+ - 100%	TS	TS	TS	TS	TS	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Exelerate [™] CSD 15	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Exelerate [™] HS - 1%	TS	TS	TS	TS	TS	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Exelerate [™] HS - 100%	TS	TS	TS	TS	TS	NR	NR	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	SD	TS	TS	TS	TS
Ecolab Exelerate [™] Tufsoil	TS	TS	TS	TS	TS	SD	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Foam Shine - 5%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	NR	TS	TS	TS	TS
Ecolab Foam Shine - 100%	TS	TS	TS	TS	TS	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	OK	TS	NR	TS	TS	TS	TS
Ecolab General Purpose Degreaser - 5%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab General Purpose Degreaser - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Klenz Solv - 2%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Klenz Solv - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	SD	TS	OK	TS	TS	TS	TS
Ecolab Lift RT - 2%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Lift RT - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS			EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY-LICS	
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST (CRYLAFLOR)	
Ecolab Mandate [™] Plus - 2%	TS	TS	TS	TS	TS	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	SD	TS	TS	TS	TS
Ecolab Mandate [™] Plus - 100%	TS	TS	TS	TS	TS	NR	NR	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	SD	TS	NR	TS	TS	TS	TS
Ecolab Neutral Disinfectant Cleaner (NDC) - 0.5 oz/gal	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	SD	TS	TS	TS	TS	OK	TS	TS	OK	TS	SD	SD	OK	OK
Ecolab Neutral Disinfectant Cleaner (NDC) - 100%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	SD	TS	TS	TS	TS	OK	TS	TS	OK	TS	SD	SD	OK	OK
Ecolab Octave FS - 2.10%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	SD	TS	TS	TS	TS
Ecolab Octave FS - 100%	TS	TS	TS	TS	TS	NR	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	OK	TS	NR	TS	TS	TS	TS
Ecolab Quorum [™] Clear V - 3%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Quorum [™] Clear V - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Soil Off II - 5%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Soil Off II - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Ster-Bac [™] - 2%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Ster-Bac [™] - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Synergic - 1%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Synergic - 100%	TS	TS	TS	TS	TS	SD	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Ultrasil [™] - 1%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Ultrasil [™] - 100%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Vortexx [™] - 1%	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab Vortexx [™] - 100%	TS	TS	TS	TS	TS	NR	NR	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	OK	TS	SD	TS	TS	TS	TS
Ecolab Wash ‘n Walk 14278	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	SD	NR	TS
Ecolab XY-12 [®] - 0.5%	TS	TS	TS	TS	TS	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	OK	TS	TS	TS	TS
Ecolab XY-12 [®] - 100%	TS	TS	TS	TS	TS	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK	TS	SD	TS	TS	TS	TS
EEP Solvent	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	NR	SD	NR	NR
Enforce LP (6000 ppm)	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	SD	TS	TS	OK	TS	SD	SD	OK	OK
Envirocid - 100%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	NR	TS	TS	SD	TS	SD	NR	NR	NR
Ethanol - 95%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	SD	TS	SD	SD

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
*Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
TS = Contact Tech Service Department

NR = Not recommended
† = May cause discoloration

				BROADCAST SYSTEMS		EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY-LICS
		RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST	MMA COATINGS (CRYLAFLO [™])
Ethoxy Ethanol	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Ethoxylated Nonyl Phenol	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Ethyl Acetate	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	SD
Ethyl Acrylate	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Ethyl Alcohol	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	NR	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Ethylamine	TS	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Ethyl Bromide	TS	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Ethyl Chloride	TS	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Ethyl Chloroformate	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Ethyl Ether	SD	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Ethyl Hexyl Acrylate	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Ethylene Dichloride	TS	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Ethylene Glycol	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	TS	TS	TS	TS	SD	OK	OK	OK	OK	SD	OK	OK	TS	TS	TS	TS	TS
Ethylene Oxide (Dilute)	SD	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Ethyl Sulfate	SD	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Excellerate Cleaner	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	OK
Ferric Chloride	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Ferric Nitrate	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Ferric Sulfate	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Fluoboric Acid	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Fluosilicic Acid - 25%	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Formaldehyde	TS	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Formaldehyde - 37%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	SD	SD	TS	SD	TS	TS	SD	OK	SD	SD	SD	SD
Formic Acid	TS	TS	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Furfural to 10%	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
*Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
TS = Contact Tech Service Department

NR = Not recommended
† = May cause discoloration

	BROADCAST SYSTEMS			EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY- LICS	
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKESB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENTE-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)		POLY-CRETE COLOR FAST
Gasoline	SD	OK	OK	SD	SD	SD	SD	OK	OK	SD	SD	SD	OK	OK	OK	TS	SD	OK	OK	OK	OK	SD	SD	OK	TS	OK	OK	OK
Aviation	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Diesel	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	OK	OK	OK	TS	SD	OK	TS	TS	OK	SD	TS	OK	TS	OK	OK	OK
Jet Fuel	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	OK	OK	OK	TS	SD	OK	TS	TS	OK	SD	TS	OK	TS	OK	OK	OK
Premium Unleaded	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Unleaded	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Glucose	SD	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Glycerine	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Glycol Ether	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK
Glycolic Acid to 70%	SD	TS	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Gold Plating (Cyanide)	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Grape Juice	SD	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Green Liquor (Paper Industry)	SD	TS	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Heating Oil Home	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	TS	OK	TS	OK	OK	OK
Heptane	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Heptanoic Acid - 96%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	NR	TS	TS
Hexane	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	NR	NR	NR	TS	OK	OK	TS	TS	OK	OK	TS	OK	TS	OK	OK	OK
Hibiclen - 4%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	SD	TS	TS	TS	TS	OK	TS	TS	SD	TS	OK	SD	OK	OK
Hydraulic Fluid	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	OK
Hydrazine - 35%	NR	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Hydrazine Hydrate	NR	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Hydriodic Acid - 20%	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Hydrobromic Acid - 20%	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Hydrobromic Acid - 48%	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Hydrochloric Acid - 5%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	OK
Hydrochloric Acid - 10%	SD	TS	TS	SD	OK	SD	SD	TS	TS	TS	TS	OK	TS	TS	TS	TS	SD	OK	OK	TS	OK	SD	TS	OK	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS			EPOXY COATINGS													URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS		
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKESB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENTE-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST (CRYLAFLOR)		
Hydrochloric Acid - 20%	TS	OK	OK	SD	OK	SD	SD	OK	OK	SD	SD	SD	SD	SD	TS	SD	OK	OK	SD	SD	SD	SD	SD	OK	TS	SD	SD	SD	
Hydrochloric Acid - 37%	TS	TS	TS	SD	OK	SD	SD	TS	TS	TS	TS	TS	NR	NR	NR	TS	SD	OK	TS	TS	SD	SD	TS	SD	OK	SD	SD	SD	
Hydrofluoric Acid - 1-10%	TS	TS	TS	OK	NR	OK	OK	TS	TS	TS	TS	TS	NR	NR	NR	TS	SD	OK	TS	TS	NR	SD	TS	TS	TS	SD	SD	SD	
Hydrofluoric Acid - 20%	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Hydrofluoric Acid - 21-48%	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	NR	NR	NR	TS	SD	SD	TS	TS	NR	SD	TS	TS	TS	TS	NR	NR	NR
Hydrofluosilic Acid - 10%	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Hydrofluosilic Acid - 30%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	OK	OK	OK	
Hydrofluosilic Acid - 35%	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Hydrogen Peroxide - 25%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	SD	TS	TS	SD	TS	OK	OK	OK		
Hydrogen Peroxide - 30%	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Hydrogen Peroxide - 35%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS		
Hydrogen Peroxide - 50%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	SD	TS	TS	TS	TS	SD	TS	TS	SD	TS	OK	NR	OK		
Hydrogen Peroxide (VHP) - 560 ppm	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	OK	TS	TS	TS	OK		
Hydrogen Sulfide Gas	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Hypo (Photographic Solution)	SD	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Hypochlorous Acid	NR	TS	TS	NR	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	
IO-Star	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	SD	SD		
Iodine	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Iodine, Crystals and Vapor	NR	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Iodine Tincture - 2%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	SD	SD		
Isooctyl Thioglycolate	SD	TS	TS	SD	TS	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Isophorone	NR	TS	TS	NR	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	
Isopropyl Acetate	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	SD	SD	SD	TS	SD	SD	TS	TS	TS	TS	SD	TS	TS	TS	SD	TS	NR	
Isopropyl Alcohol	SD	OK	OK	OK	SD	OK	SD	OK	OK	OK	OK	SD	SD	SD	SD	SD	OK	OK	OK	OK	OK	SD	OK	OK	TS	SD	OK	SD	
Isopropyl Ether	NR	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Jet Fuel JP-4	SD	OK	OK	SD	SD	SD	OK	OK	OK	SD	SD	SD	TS	TS	TS	TS	SD	OK	OK	OK	TS	SD	SD	TS	TS	TS	TS	TS	

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
*Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
TS = Contact Tech Service Department

NR = Not recommended
† = May cause discoloration

	BROADCAST SYSTEMS				EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS	
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST (CRYLAFLOR)	
Kay Chemical Remover Plus NTF Degreaser (10.4%)	SD	SD	SD	OK	TS	SD†	TS	TS	TS	TS	TS	OK	TS	SD	TS	TS	TS	TS	OK	TS	OK	OK	TS	SD†	OK	SD†	OK	TS
Kennel Care (Provet Logic Floor Cleaner) - 100%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	OK
Kerosene	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Ketchup	OK	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Lactic Acid - 10%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	OK	TS	TS	SD	TS	OK	OK	OK	OK
Lactic Acid - 30%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	SD	TS	TS	SD	TS	OK	SD	OK	OK
Lactic Acid - 88%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	NR	TS	TS	NR	TS	OK	SD	OK	OK
Lactic Acid Concentrated	SD	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Lard	SD	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Lauric Acid	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Lauryl Chloride	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Lead Acetate	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Lecithin	SD	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Levulinic Acid (Saturated)	SD	TS	TS	SD	SD	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Linseed Oil	SD	TS	TS	TS	SD	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Lithium Hydroxide - 10%	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Lithium Hydroxide (Saturated)	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Liquinox®	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS
LpH III SE	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	SD	TS	TS	NR	TS	TS	TS	TS
LpH III SE - Dilute	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	OK	TS	TS	OK	TS	TS	TS	TS
Luperox® DHD-9	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Maleic Acid	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Malic Acid	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Magnesium Hydroxide	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	OK	OK
MEK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	SD	OK	TS	OK	TS	TS	OK	TS	NR	SD	NR

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS				EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY- LICS
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST	MMA COATINGS (CRYLAFLOR)
MEKP	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	SD	TS	TS	SD	TS	TS	TS	TS
Mercury and Salts	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Methacrylate Monomer	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	NR	NR	NR	NR
Methanol - 100%	SD	TS	TS	OK	NR	OK	OK	TS	TS	TS	TS	NR	NR	NR	NR	TS	SD	SD	TS	TS	OK	SD	TS	OK	TS	NR	SD	NR
Methyl Acetate	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Methyl Cellosolve	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	NR
Methyl Dipropasol Solvent	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	NR
Methyl Chloride	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS
Methyl Ethyl Ketone	NR	OK	OK	OK	SD	OK	SD	SD	SD	SD	SD	TS	TS	TS	TS	TS	SD	OK	OK	OK	TS	SD	SD	TS	TS	TS	TS	TS
Methyl Isobutyl Ketone	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Methyl Oleate	SD	TS	TS	SD	OK	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Methylamyl Alcohol	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Methylene Chloride	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	NR	NR	NR	NR	TS	NR	SD	TS	TS	TS	NR	TS	TS	TS	NR	SD	NR
MIBK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	NR	NR	NR	NR
Milk - Fresh and Sour	SD	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Mineral Oil	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	OK
Mineral Spirits	SD	OK	OK	SD	SD	SD	OK	OK	OK	OK	OK	SD	SD	SD	TS	TS	SD	OK	OK	OK	OK	SD	OK	OK	TS	OK	OK	OK
Molasses	OK	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Monoethanolamine	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Motor Oil	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	OK	OK	TS	OK	TS	TS	OK	TS	OK	OK	OK
Muratic Acid	SD	TS	TS	SD	SD	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Mustard, Yellow	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	NR	TS	TS	TS	TS	TS	SD	TS	TS	OK	TS	SD	SD	OK	OK
N-Butyl Acetate	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	OK	TS	TS	OK	TS	TS	TS	TS
Naphtha - Aliphatic	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Naphtha - Aromatic (Coal Tar)	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Naphthalene (in Benzene)	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS				EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS		
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKESB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST	MMA COATINGS (CRYLAFLOR)	
Naphthenic Acid	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Nickel Chloride	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	SD	SD	SD	SD
Nickel Plating, Bright	TS	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Nickel Sulfate	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	SD	SD	SD	SD
Nitric Acid - 5%	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	OK	TS	TS	TS	TS
Nitric Acid - 10%	TS	SD	SD	OK	SD	OK	SD	SD	SD	SD	NR	SD	SD	SD	SD	TS	SD	SD	SD	NR	SD	SD	NR	SD	OK	SD	SD	SD	SD
Nitric Acid - 20%	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	SD	TS	TS	NR	TS	SD	SD	SD	SD	SD
Nitric Acid - 25%	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Nitric Acid - 30%	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	NR	TS	TS	NR	TS	SD	SD	SD	SD	SD
Nitric Acid - 40% [†]	TS	TS	TS	OK [†]	NR	OK [†]	SD	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	NR	TS	TS	NR	NR	SD	SD	SD	NR	NR
Nitric Acid - 60% [†]	TS	TS	TS	OK [†]	NR	OK [†]	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS
Nitric Acid - 70% [†]	TS	TS	TS	OK [†]	NR	OK [†]	NR	TS	TS	TS	TS	NR	NR	NR	TS	TS	NR	NR	TS	NR	TS	TS	NR	NR	NR	NR	NR	NR	NR
Nitric Acid - 73% [†]	TS	TS	TS	OK [†]	NR	OK [†]	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Nitric Acid - 89%	TS	TS	TS	NR	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Nitric Acid - 98%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	NR	TS	TS	NR	TS	NR	NR	NR	NR	NR
Nitrioltriethanol	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Nitrobenzene	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Nitromethane	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Octanol	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Oils	SD	TS	TS	NR	SD	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Animal	SD	TS	TS	NR	SD	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Mineral	SD	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sour Crude Petroleum	SD	TS	TS	NR	SD	NR	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Vegetable	SD	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Oleic Acid	SD	TS	TS	SD	TS	SD	SD	TS	TS	TS	TS	SD	OK	OK	OK	TS	OK	OK	TS	TS	OK	OK	TS	OK	TS	OK	OK	OK	OK
Oxalic Acid (Saturated)	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
*Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
TS = Contact Tech Service Department

NR = Not recommended
† = May cause discoloration

	BROADCAST SYSTEMS				EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS	
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST (CRYLAFLOR)	MMA COATINGS (CRYLAFLOR)
Oxalic Acid - 10%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	OK
Para Xylene	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Pelargonic Acid	TS	TS	TS	OK	TS	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Pentachloroethane	SD	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Peppermint Oil - 100%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	SD	TS	TS	OK	TS	OK	OK	TS	TS
Peracetic Acid, 39% in Acetic Acid - 3%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	SD	TS	TS	OK	TS	SD	SD	OK	TS
Perchloric Acid - 30%	TS	TS	TS	TS	NR	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Perchloroethylene	TS	TS	TS	SD	NR	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Peroxigard [™]	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	SD	NR	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	SD	SD	SD
Phenol - 5%	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Phenol - 85%	TS	TS	TS	TS	NR	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Phenol Sulfonic Acid - 65%	NR	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Phenolic Paint Stripper Waste 1-5%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR
Phosphoric Acid - 7%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	NR	TS	TS	NR	TS	OK	OK	OK	OK
Phosphoric Acid - 10%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	OK	TS	TS	OK	TS	TS	TS	TS
Phosphoric Acid - 20%	SD	SD	SD	OK	SD	OK	SD	SD	SD	SD	SD	SD	TS	TS	TS	TS	SD	OK	SD	SD	TS	SD	SD	TS	TS	TS	TS	TS
Phosphoric Acid - 25%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	SD	TS	OK	OK	TS	OK	TS	TS	OK	TS	OK	OK	OK
Phosphoric Acid - 50%	NR	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	NR	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS
Phosphoric Acid - 85%	NR	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	NR	NR	NR	TS	SD	SD	TS	TS	NR	SD	TS	NR	TS	NR	NR	SD	SD
Phosphorous Oxychloride	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Phosphorous Trichloride	TS	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	NR	NR	NR	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR
Picric Acid - 10% (in Alcohol)*	TS	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
PM Solvent	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	SD	SD	NR	NR
Polyacrylic Acid - 50%	SD	TS	TS	SD	TS	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Polyester Resin	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD
Polyester Resin in Styrene	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

				BROADCAST SYSTEMS			EPOXY COATINGS											URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY- LICS
				RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	
Polyphosphates	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	OK		
Potassium Acetate	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Potassium Bichromate	SD	TS	TS	SD	OK	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Potassium Bromide	SD	TS	TS	SD	OK	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Potassium Carbonate - 25%	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Potassium Chlorate	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Potassium Chloride	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Potassium Cyanide	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	SD	SD	SD	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	SD	
Potassium Fluoride	SD	TS	TS	SD	TS	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Potassium Hydroxide - 10%	SD	TS	TS	SD	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Potassium Hydroxide - 45%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	OK	
Potassium Hydroxide - 50%	SD	TS	TS	SD	OK	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Potassium Nitrate	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Potassium Permaganate	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Potassium Permaganate - Solid	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	SD		
Potassium Persulfate	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Potassium Sulfate	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Process NPD® One-Step Germicidal Detergent	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
ProKlenz® NpH	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	
Propanediol	TS	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Propionic Acid - 3%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	OK	
Propionic Acid - 100%	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	SD	SD	SD	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	
Propyl Acetate	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	NR	NR	
Propyl Cellosolve	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS		
Propylene Glycol	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	OK	OK	OK	TS	SD	OK	TS	TS	OK	SD	TS	OK	TS	OK	OK	OK	OK	
Propylene Glycol Ether	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	OK	TS	TS	OK	TS	SD	SD	OK	OK		

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
*Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
TS = Contact Tech Service Department

NR = Not recommended
† = May cause discoloration

	BROADCAST SYSTEMS				EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS	
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKESB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST (CRYLAFLOR)	
Pyridine	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Rayon Spin Liquor	SD	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Red Wine Vinegar	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	SD	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	SD	OK	OK
Remedy	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	SD	OK	OK	OK
Salicylaldehyde	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Salicylic Acid	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Salt Brine	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Sani Clean	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	SD	OK	OK
Septhiol - 70%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Silicon Tetrachloride	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Silver Cyanide	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Silver Nitrate	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Silver Nitrate - 5%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	SD	TS	TS	OK	TS	SD	SD	SD	SD
Silver Nitrate - 20%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	SD	SD	SD
Simple Green®	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	OK	TS	TS	OK	OK	TS	TS	TS	TS
Simulated Seawater (Instant Ocean)	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	OK	TS	TS	OK	TS	TS	TS	TS	TS
Skydrol™	TS	OK	OK	OK	NR	OK	SD	SD	NR	NR	SD	NR	SD	SD	SD	SD	SD	OK	OK	OK	SD	NR	SD	TS	TS	OK	OK	OK
Sodium Acetate	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Bicarbonate	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Bisulfate	SD	TS	TS	SD	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Bisulfite	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Bromate	SD	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Carbonate (Saturated)	SD	TS	TS	NR	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Chlorate	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Chloride	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	OK	OK	OK	OK	TS	OK	OK	TS	TS	OK	OK	TS	OK	OK	OK	OK	OK
Sodium Chlorite (Saturated)	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS				EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE		ACRY- LICS
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST (CRYLAFLOR)	
Sodium Chromate	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Cyanide - 15%	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Dichromate	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Fluoride	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Hydrosulfide - 45%	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Hydroxide - 10%	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	TS	TS	TS	TS	OK	OK	OK	OK	OK	OK	OK	OK	OK	TS	TS	TS	TS
Sodium Hydroxide - 50%	SD	OK	OK	OK	OK	OK	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	TS	OK	OK	OK
Sodium Hypochlorite - 3%	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Sodium Hypochlorite - 5%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	SD	TS	TS	OK	TS	OK	OK	OK	OK
Sodium Hypochlorite - 15%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	SD	TS	TS	OK	TS	SD	SD	OK	OK
Sodium Hypochlorite - 17%	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Sodium Hypochlorite - 50%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	SD	TS	TS	OK	TS	SD	SD	OK	OK	OK
Sodium Hypochlorite - 100%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	SD	OK	OK	OK
Sodium Lauryl Sulfate - 20%	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Sodium Oxalate	TS	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Peroxide - Peroxide Bleach	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Sodium Persulfate	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	SD
Sodium (Acid) Phosphate	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Sodium Phosphate (Tri)	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Polymethacrylate	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Sulfate	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Sulfide (Saturated)	SD	TS	TS	OK	OK	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Sulfite	SD	TS	TS	OK	OK	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Tartrate	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Sodium Thiosulfate (Hypo)	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS
Soybean Oil	SD	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS				EPOXY COATINGS												URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS	
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST (CRYLAFLOR)	
Spartan, Inspector's Choice®, 6 oz/gal - 5%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	SD	SD	TS	TS	TS	TS	OK	TS	TS	TS	OK	TS	OK	OK	OK
Spartan, SparClean® Sure Step®, 2 oz/gal - 1.5%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	SD	NR	OK	
Spearmint Oil	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	NR	NR	
Spor-Klenz® - 0.3%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	SD	TS	TS	OK	TS	OK	OK	OK	
Spor-Klenz® Concentrate	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	SD	TS	TS	SD	SD	TS	TS	TS
Spor-Klenz® Ready-to-Use	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	OK	TS	TS	OK	SD	TS	TS	TS
Stannic Chloride	SD	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Stannous Chloride	SD	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Star San	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	SD	OK	
Stearic Acid	SD	TS	TS	SD	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Steris CIP 200™	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS
Steris Coverage® Plus NPD®	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Steris Coverage® Spray HB Plus Ready-to-Use Cleaner	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Steris Vesta-Syde® SQ	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	
Stoddard Solvent	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	NR	
Stride	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	SD	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	SD	SD	OK	
Styrene	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	NR	NR	NR	TS	SD	OK	TS	TS	TS	TS	SD	TS	TS	NR	TS	NR	
Sugar	SD	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Sulfamic Acid - 25%	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	
Sulfite Liquor (Paper Industry)	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	
Sulfonic Acid - 70%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	NR	TS	
Sulfur Dioxide (Wet)	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	
Sulfur Trioxide (Wet)	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	TS	TS	TS	TS	
Sulfuric Acid - 10%	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	SD	SD	SD	TS	SD	OK	OK	TS	SD	SD	SD	TS	SD	SD	SD	SD	
Sulfuric Acid - 25%	TS	SD	SD	OK	SD	OK	SD	SD	SD	SD	SD	TS	TS	TS	TS	SD	SD	SD	SD	SD	SD	SD	SD	TS	TS	TS	TS	

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS			EPOXY COATINGS													URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS	
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENTE-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST	MMA COATINGS (CRYLAFLOR)
Sulfuric Acid - 30%	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	NR	NR	NR	TS	TS	TS	TS	SD	TS	TS	SD	TS	SD	NR	SD	
Sulfuric Acid - 50% [†]	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	NR	NR	NR	TS	SD	SD	SD	TS	NR	SD	TS	SD	TS	SD	NR	SD
Sulfuric Acid - 70% [†]	TS	TS	TS	OK [†]	NR	OK [†]	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS
Sulfuric Acid - 90-98% [†]	NR	TS	TS	OK [†]	NR	OK [†]	NR	TS	TS	TS	TS	TS	NR	NR	NR	TS	NR	NR	TS	TS	NR	NR	TS	NR	TS	NR	NR	NR
Super Shine-All [®]	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	
Tall Oil	TS	TS	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Tannic Acid - 20%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	
Tartaric Acid	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	
Tartaric Acid - 10%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	
Terpene Fraction of Spearmint Oil - 100%	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	
Tetrachloroethane	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Tetrachloroethylene	TS	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Tetrahydrofuran	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Tetrahydrofurfuryl Alcohol	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Thionyl Chloride	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Thionyl Chloride - Water Solution*	TS	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Toluol	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	NR	NR	NR	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	SD	TS	
Toluene Sulfonic Acid	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Toluidine	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Top Guard [™]	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	SD	TS	TS	TS	TS	TS	OK	TS	TS	SD	TS	SD	SD	OK	
Transmission Fluid	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	SD	TS	TS	OK	OK	TS	OK	TS	TS	OK	TS	OK	OK	OK	
Trichloroacetic Acid - 20%	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Trichlorobenzene (1,2,4-)	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Trichloroethane	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Trichloroethane (1,1,1)	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Trichloroethylene	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	NR	NR	NR	TS	TS	SD	TS	TS	OK	TS	TS	TS	TS	NR	SD	TS	

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
*Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
TS = Contact Tech Service Department

NR = Not recommended
† = May cause discoloration

	BROADCAST SYSTEMS			EPOXY COATINGS													URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS		
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKESB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC	RESUFLO [™] 3746 SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT	RESUFLO [™] MPE MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST (CRYLAFLOR)		
Tricresyl Phosphate - 100%	TS	TS	TS	SD	OK	SD	NR	TS	TS	TS	TS	OK	TS	TS	TS	SD	OK	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Triethanolamine (TEA)	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	
Triethanolpentamine (TEPA)	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Triethanoltetramine (TETA)	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Triethyl Phosphite	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Triethylamine	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Triethylenetetramine	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Trisodium Phosphate (Saturated)	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Turbo Charge II NP	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	TS	OK	TS	OK	OK	OK	
Turpentine	TS	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	
Urea Solutions	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Urine	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	OK	
Vesphene® II st - 2 oz/2 gal	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	SD	SD	TS	SD	OK	TS	OK	TS	TS	OK	TS	SD	SD	SD	
Vesphene® III st	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	SD	TS	TS	SD	OK	TS	TS	TS	
Vinegar	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
Vinyl Chloride	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Virex®	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	SD	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	SD	OK	OK	
Vortexx [™] (2600 ppm)	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	TS	TS	SD	TS	TS	OK	TS	SD	SD	OK	OK	
Water	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	
Water, Deionized	SD	OK	OK	SD	OK	SD	SD	OK	OK	OK	OK	OK	TS	TS	TS	TS	OK	SD	OK	OK	TS	OK	OK	TS	TS	TS	TS	TS	
Water, Distilled & Demineralized	SD	OK	OK	OK	OK	OK	SD	OK	OK	OK	OK	OK	TS	TS	TS	TS	OK	OK	OK	OK	TS	OK	OK	TS	TS	TS	TS	TS	
White Liquor (Paper Industry)	SD	TS	TS	SD	OK	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	
White Vinegar	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	TS	OK	TS	TS	OK	TS	OK	OK	OK	OK	
Windex®	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	
Wine	SD	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Wine, Red	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	SD	TS	TS	TS	TS	SD	TS	TS	OK	TS	OK	SD	OK	OK	

OK = Recommended for exposure not to exceed 72 hours prior to cleaning
 *Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily
 TS = Contact Tech Service Department

NR = Not recommended
 † = May cause discoloration

	BROADCAST SYSTEMS				EPOXY COATINGS											URETHANE COATINGS					POLYASPARTIC/ FAST CURE COATINGS				URETHANE CONCRETE	ACRY- LICS
	RESUFLO [™] TOPFLOOR SL23	RESUFLO [™] DECO QUARTZ DB23	RESUFLO [™] DECO FLAKE SB	RESUFLO [™] 3725	RESUFLO [™] 3555	RESUFLO [™] 3741 NOVOLAC SELF-LEVELING	RESUFLO [™] CRN NOVOLAC	RESUFLO [™] PT 250 TOPCOAT MULTI-PURPOSE	RESUFLO [™] GPE GENERAL PURPOSE	RESUFLO [™] UVE UV-RESISTANT	RESUFLO [™] GARD	RESUFLO [™] GLAZE	RESUFLO [™] ULTRA	RESUFLO [™] VENT-E	RESUTILE [™] 4638	RESUTILE [™] 4685	RESUTILE [™] HPS 100 AND HTS 100	RESUTILE [™] SDS STATIC DISSIPATIVE	RESUTILE [™] AT	ACCELERA [™] 4850	ACCELERA [™] 5	ACCELERA [™] (REGULAR, EXT, LH)	ACCELERA [™] ONE	POLY-CRETE (HF, MD, TF PLUS)	POLY-CRETE COLOR FAST (CRYLAFLOR)	MMA COATINGS (CRYLAFLOR)
Xylene	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	SD	TS	TS	SD	OK	TS	OK	TS	TS	OK	TS	SD	SD	NR
Xylol	TS	OK	OK	SD	SD	SD	NR	OK	OK	SD	SD	SD	TS	TS	TS	SD	SD	OK	OK	TS	SD	OK	TS	TS	TS	TS
Zinc Plating - Acid Fluoborate	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Zinc Plating - Acid Sulfate	SD	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS
Zinc Plating - Cyanide	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS

THE SHERWIN-WILLIAMS DIFFERENCE

Sherwin-Williams High Performance Flooring delivers world-class industry subject matter expertise, unparalleled technical and specification service, and unmatched regional commercial team support to our customers around the globe.

OK = Recommended for exposure not to exceed 72 hours prior to cleaning

*Requires additional considerations; contact Tech Service Department

SD = Splash/spillage daily

TS = Contact Tech Service Department

NR = Not recommended

† = May cause discoloration